



US007494580B2

(12) **United States Patent**
Sandoval et al.

(10) **Patent No.:** **US 7,494,580 B2**
(45) **Date of Patent:** ***Feb. 24, 2009**

(54) **SYSTEM AND METHOD FOR PRODUCING COPPER POWDER BY ELECTROWINNING USING THE FERROUS/FERRIC ANODE REACTION**

(75) Inventors: **Scot P Sandoval**, Morenci, AZ (US); **Antonioni C Stevens**, Thatcher, AZ (US); **Timothy G Robinson**, Scottsdale, AZ (US); **John O Marsden**, Phoenix, AZ (US); **Stanley R Gilbert**, Thatcher, AZ (US)

(73) Assignee: **Phelps Dodge Corporation**, Phoenix, AZ (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 131 days.

This patent is subject to a terminal disclaimer.

(21) Appl. No.: **11/160,910**

(22) Filed: **Jul. 14, 2005**

(65) **Prior Publication Data**

US 2005/0269209 A1 Dec. 8, 2005

Related U.S. Application Data

(63) Continuation-in-part of application No. 10/629,497, filed on Jul. 28, 2003, now Pat. No. 7,378,011.

(60) Provisional application No. 60/590,882, filed on Jul. 22, 2004.

(51) **Int. Cl.**
C25C 1/12 (2006.01)

(52) **U.S. Cl.** **205/576; 205/574; 205/575; 205/580; 205/583; 205/584**

(58) **Field of Classification Search** **205/574, 205/575, 576, 580, 583, 584**
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

2,792,342 A *	5/1957	Tuwiner	205/577
3,262,870 A	7/1966	Harlan		
3,616,277 A	10/1971	Adamson et al.		
3,876,516 A	4/1975	Pace et al.		
3,887,396 A	6/1975	Walsh et al.		
3,915,834 A	10/1975	Wright et al.		
3,956,086 A	5/1976	Wilkinson et al.		
3,972,795 A *	8/1976	Goens et al.	204/269
4,071,431 A	1/1978	Nicou et al.		
4,129,494 A *	12/1978	Norman	204/268
4,219,401 A	8/1980	Johnson		
4,226,685 A	10/1980	Portal et al.		
4,272,339 A	6/1981	Knight et al.		
4,278,521 A	7/1981	Kreysa		
4,292,160 A	9/1981	Marcantonio		
4,318,789 A	3/1982	Marcantonio		
4,373,654 A	2/1983	Prengaman et al.		
4,399,020 A	8/1983	Branchick et al.		

4,436,601 A	3/1984	Branchick et al.		
4,445,990 A	5/1984	Kim et al.		
4,515,672 A	5/1985	Platek et al.		
4,556,469 A	12/1985	Kim et al.		
4,560,453 A	12/1985	Hoffman et al.		
4,680,100 A	7/1987	Morin		
4,715,934 A	12/1987	Tamminen		
4,762,603 A	8/1988	Morin		
4,776,941 A	10/1988	Tezanos et al.		
4,789,450 A	12/1988	Paterson		
4,834,850 A	5/1989	deNora et al.		
4,863,580 A	9/1989	Epner		
4,960,500 A	10/1990	Epner		
5,006,216 A	4/1991	Dietrich et al.		
5,133,843 A	7/1992	Eisman		
5,292,412 A	3/1994	Pitton		
5,324,409 A	6/1994	Mayr et al.		
5,368,702 A	11/1994	deNora		
5,454,917 A	10/1995	Mattison et al.		
5,458,746 A	10/1995	Burgess et al.		
5,492,608 A *	2/1996	Sandoval et al.	204/237

(Continued)

FOREIGN PATENT DOCUMENTS

CA 1162514 2/1984

(Continued)

OTHER PUBLICATIONS

Alkire, R., et al., "Flow Through Porous Electrodes;" J. Electrochem Soc.; 122, 1594; 1975.

Marracino, J.M., et al., "A First Investigation of Flow-Through Porous Electrodes Made of Metallic Felts or Foams;" Electrochim. Acta; 32, 1303; 1987.

Popov, K. I., et al., "The Comparison of Galvanostatis . . . Aluminium Electrodes;" Journal of Applied Electrochemistry, V. 8, pp. 503-514.

Qi, J. et al., "Analysis of Flow-Through Porous Electrode . . .;" J. Appl. Electrochem.; 23, 873; 1993.

Saleh, M.M., et al., "Electrowinning of Non-Noble Metals with Simultaneous Hydrogen Evolution at Flow-Through Porous Electrodes;" J. Electrochem. Soc.; 142, 4122; 1995.

Smirnov, B. N., et al., "Mechanism of the Cathodic . . .;" Trans. from Porosh. Metallurgiya, No. 3 (291), pp. 1-4 (1987) (Orig. article submit Mar. 25, 1986).

(Continued)

Primary Examiner—Bruce F Bell
(74) *Attorney, Agent, or Firm*—Snell & Wilmer L.L.P.

(57) **ABSTRACT**

The present invention relates, generally, to a method for electrowinning copper powder, and more particularly to a method for electrowinning copper powder from a copper-containing solution using the ferrous/ferric anode reaction. In accordance with various embodiments of the present invention, a process for producing copper powder by electrowinning employs alternative anode reaction technology, namely, the ferrous/ferric anode reaction, and enables the efficient and cost-effective production of copper powder at a total cell voltage of less than about 1.5 V and at current densities of greater than 50 A/ft². A copper powder electrowinning process in accordance with the present invention also reduces or eliminates acid mist generation that is characteristic of electrowinning operations utilizing conventional electrowinning chemistry (e.g., oxygen evolution at the anode), which is advantageous.

13 Claims, 9 Drawing Sheets