

UNITED STATES PATENT OFFICE

2,097,446

PHOSPHATE-SULPHUR FERTILIZER AND PROCESS OF MAKING SAME

John T. Claiborne, Jr., New York, N. Y., and Paul D. Peterson, New Brunswick, N. J., assignors, by mesne assignments, to Freeport Sulphur Company, a corporation of Delaware

No Drawing. Application December 21, 1935,
Serial No. 55,564

14 Claims. (Cl. 71-33)

The present invention relates to fertilizer compositions, more particularly a fertilizer composition formed from phosphate rock and sulphur, and the process of making the same.

5 General objects of the invention are the provisions of such a fertilizer composition in a form which efficiently remains in an available state in soil for an unusually long period of time and allows the acid formed by gradual oxidation of the sulphur to act freely with the surrounding phosphate without interference with soil bases; and an efficient, simple, unusually cheap and readily practiced process of making the fertilizer composition.

15 A more specific object of the invention is the provision of such a composition in pellet form efficiently resistant to fracture wherein each pellet, which is preferably porous, constitutes a mass of phosphate particles bound together by fused sulphur distributed throughout the interior of the pellet, and an efficient and simple process whereby molten sulphur is mixed with phosphate rock particles to bind them together and the resultant mixture is readily subdivided into particles by pelletizing while the sulphur is in the molten state.

Other objects of the invention will in part be obvious and will in part appear hereinafter.

20 The invention accordingly comprises the several steps and the relation of one or more of such steps with respect to each of the others, and the product possessing the features, properties, and the relation of constituents, which are exemplified in the following detailed disclosure, and the scope of the invention will be indicated in the claims.

25 In accordance with the present invention phosphate rock particles are mixed with molten sulphur and the resultant mixture is pelletized to form pellets with sulphur binding the phosphate rock particles together. This is preferably accomplished by pouring or spraying molten sulphur into a mass of finely divided and preferably preheated phosphate rock particles of a size that will pass through a screen of 20 mesh or more, preferably about 100 mesh for obtaining a greater contact surface between the phosphate rock particles and the sulphur. The mixture is then stirred in any suitable mixer of proper design and is subdivided into particles by pelletizing while the sulphur is in a molten state.

30 The amount of sulphur preferably constitutes between about 20 and 30 per cent of the mixture so that porous pellets are obtained. Although this is the preferred range of the amount of sul-

phur, with the use of improved mixing equipment it may be possible in the practice of the present invention to lower the amount of sulphur, for example, to amounts as low as 10 or 15 per cent. Amounts of sulphur greater than 20 to 30 per cent may also be used in the production of pelletized phosphate-sulphur fertilizer when porosity is of less importance than other features. Such a composition having a high percentage of sulphur, e. g. 50 per cent or more, would be useful as a soil amendment in the treatment of alkaline soils, the excess sulphur being oxidizable into sulphuric acid for making the soil less alkaline and thus more suitable for plant growth.

35 The mixture is pelletized by passing it while the sulphur is in a molten state through apertures of a suitable device such as an extruding device, or a screen of relatively large mesh, e. g. about 8 mesh. It has been found that if the mixture while the sulphur is in a molten state is passed through such apertures at the temperature of the dark viscous stage of the sulphur, e. g. between about 160° C. and 260° C., preferably at a temperature between about 220° C. and 260° C., the mixture will, as it emerges from the apertures, break up into pellets. As sulphur is heated to increasing temperatures it melts forming a pale-yellow, mobile liquid and then undergoes further changes. When the melted sulphur is heated until a temperature of from about 156° C.-162° C. is reached the pale-yellow, mobile liquid suddenly becomes dark red in color and so viscous that it can be poured out of the vessel only with difficulty, if at all. Beyond 260° C. the viscosity becomes noticeably less. Reference is made to lines 14 to 18 inclusive, page 369 of Inorganic Chemistry by Alex Smith, published in 1910 by The Century Co., New York, and to lines 1 to 5 inclusive, page 382 of Treatise on Chemistry by Roscoe and Schorlemmer, Vol. 1, published in 1911 by Macmillan and Co., Ltd., St. Martin's St., London. The temperature of the dark viscous stage of molten sulphur thus varies from about 160° C. to about 260° C. Obviously after forming the mixture it may be allowed to cool and then be reheated and pelletized at the temperature of the dark viscous stage of the sulphur but preferably pelletizing is done immediately after the molten sulphur is added to the phosphate rock particles with suitable temperature control so that heat may be conserved.

45 Any suitable procedure for forming a mixture of phosphate rock particles and molten sulphur may be practiced in accordance with the present invention. Elemental sulphur in any of its several