

# UNITED STATES PATENT OFFICE

2,520,046

## BONDING TEAM FOR PROTECTION AGAINST LEAD SHEATH CORROSION

Edwin J. Merrell, Eastchester, N. Y., assignor to  
Phelps Dodge Copper Products Corporation,  
Dover, Del., a corporation of Delaware

Application October 5, 1945, Serial No. 620,587

1 Claim. (Cl. 154—2.28)

1

This invention relates to the protection of lead sheath of electric cables against corrosion and has for its object to present a bonding team employed to attach a corrosion protection to the lead sheath.

Protection of metal structures, such as the lead sheath of an electric cable, against corrosion induced by electrolysis and corrosive soil elements has been an economic necessity in many locations, despite the considerable added increment in cost entailed by conventional protection methods. However, in many more instances it would have been used to effect a conservation of materials and a continuity of service, were it not for the relatively prohibitive cost of these conventional methods of protection, not only for material, but also in trained personnel. Furthermore, the exploitation of thermoplastics in this field has been handicapped, despite their highly efficient characteristics in this respect, because no mutual bonding agent has been available which would maintain its bonding characteristic during many conditions encountered in normal usage, such as the bending and abrasion which occur when drawing cable into concrete duct systems.

I have discovered a method of overcoming this lack of a mutual agent for bonding thermoplastics to metal, which also may be applied to the bonding of other corrosion protections, for example, vulcanizates, to metal.

My invention consists essentially of a novel bonding team which is employed to attach the corrosion protection to the metal; and, furthermore, the elements of this bonding team lend necessary physical support to the protection layer. The bonding team is a combination of adhesive and fibre, the adhesive functioning as a bond between the metal and the layer of fibre, and the layer of fibre as a joining mechanism between adhesive and protection layer. The protection layer is placed over the fibre layer, and is applied in a manner such as to force it into the fibre, forming thereby a mechanical bond therewith. Not only in this way is the protection layer bonded to the lead sheath, but also in turn the manner of bonding via a fibre layer offers a most efficient physical support of the protection layer; thus, the supporting element, being concentrated at the inside surface of the protective element, permits the maximum elastic movement of the protection which is important to the prevention of damage, for example, during electric cable laying operations, and in turn the fibre layer is protected from physical and chemical damage by virtue of its totally enclosed position.

2

The adhesive employed is preferably quick setting to permit maximum production speeds. It should retain a considerable degree of elasticity when set, so as to accommodate the bending met in manufacturing and installation procedures.

The fibre layer must be characterized by relatively high porosity and flexibility, and by a moderate degree of elasticity.

While the corrosion protection layer may be either a vulcanizate or a thermoplastic, or combinations of either or both, depending upon the character of protection required, I prefer the thermoplastic, polyethylene, because of its stable characteristics with respect to time and because of its self-lubricating property. The vinyl plastics also are useful in this construction because of their oil resistance.

Where considerable waste heat energy is available, as directly after extrusion of lead sheath, hot melt adhesives, solvent type adhesives, or adhesive emulsions may be used efficiently, the waste heat driving off the solvent. When this arrangement is not feasible, polymerizing adhesives or self-curing adhesives should be used. In some instances pressure sensitive adhesives are applicable. Examples of these different types of adhesives are: hot melt, a stearin pitch; solvent, a Buna N dissolved in ethylene dichloride; emulsion, a water suspended latex; polymerizing, a plasticized mixture of monomeric and polymeric styrene; self-curing, a rubber cement to which accelerators and curing agents are added just before use; pressure sensitive, a plasticized crude rubber.

My invention is illustrated in the figure, which is a typical cross section through the bond shown in relation to the cable, in which 10 is the lead sheath, 11 the adhesive layer, 12 the fibre layer, butt wrapped, 13 the protection layer, 14 the cleats formed in the butt spaces by forcing the protection layer into the fibre layer and 15 open-butts.

Application of the fibre layer by taping is particularly advantageous, mechanically, since it provides additional longitudinal support for the corrosion protection layer due to the interlocking or cleated joint which results. Open-butt taping is preferred over lapped taping because the cleat is effective in two directions of pull, whereas that obtained in the lapped construction is effective in only one direction. Open-butt taping is the method, commonly understood in the industry, of applying tape so that a space is left between the successive turns of the tape. The fibre layer may be wood pulp paper, cotton cloth, asbestos cloth,