

[72] Inventor **Thomas Gordon Hart**
Cranbury, N.J.
 [21] Appl. No. **884,026**
 [22] Filed **Dec. 10, 1969**
 [45] Patented **Sept. 21, 1971**
 [73] Assignee **Phelps Dodge Corporation**
New York, N.Y.
Continuation of application Ser. No.
478,612, Aug. 10, 1965, now abandoned.

[54] **METHOD FOR PURIFICATION OF COPPER**
5 Claims, 9 Drawing Figs.

[52] U.S. Cl. **75/72,**
75/76
 [51] Int. Cl. **C22b 15/14**
 [50] Field of Search. **75/72-76**

[56] **References Cited**

UNITED STATES PATENTS

2,879,190	3/1959	Logan, et al.	148/1.5
2,998,335	8/1961	Dehmelt.....	148/1.6
3,501,292	3/1970	Hart	75/72

FOREIGN PATENTS

635,673 0/1928 France

OTHER REFERENCES

Morse, Richard S.: High Vacuum Technology, In Industrial and Engineering Chemistry, 99(9), p. 1064, September 1947.

Stauffer, Robert A.: Vacuum Melting and Casting of Copper, In Industrial and Engineering Chemistry, 40(5), p. 820, May 1948.

Kuhn, W. E.: Arcs in Inert Atmospheres and Vacuum, John Wiley & Sons, Inc., N.Y., 1956, pp. 41-56, by W. H. Smith Effect of Variables on The Melting Rate of Metals in the Consumable Electric Arc Furnace.

Primary Examiner—L. Dewayne Rutledge

Assistant Examiner—Joseph E. Legru

Attorney—Davis, Hoxie, Faithfull & Hapgood

ABSTRACT: Copper is refined by dissolving into the copper substantial amounts of hydrogen to aid in the removal of oxygen impurities. The molten copper is subjected to vacuum treatment to remove the excess hydrogen, thereby causing agitation of the molten copper to improve the removal of volatile impurities.