

United States Patent [19]

Bradford et al.

[11] Patent Number: 4,671,833

[45] Date of Patent: Jun. 9, 1987

[54] PROCESS FOR APPLYING A HEAT-SHRINKABLE MATERIAL OVER SULFUR WELL PIPING

[75] Inventors: **Randol W. Bradford, Waggaman; Alfred E. Hiller, Metairie; Burnham F. Winters, Jr., Thibodaux, all of La.**

[73] Assignee: **Freeport Minerals Company, New York, N.Y.**

[21] Appl. No.: 653,598

[22] Filed: Sep. 24, 1984

[51] Int. Cl.⁴ B32B 31/26

[52] U.S. Cl. 156/86; 166/244.1; 166/902; 264/230; 264/342 R; 285/45; 285/53; 285/381; 285/909

[58] Field of Search 156/86, 85; 264/230, 264/342 R; 166/244 R, 244 C; 285/45, 53, 381, DIG. 10

[56] References Cited

U.S. PATENT DOCUMENTS

3,297,819 1/1967 Wetmore 156/86
3,542,404 11/1970 Henry et al. 285/381
4,245,674 1/1981 Nakamura et al. 156/86
4,465,309 8/1984 Nimke et al. 285/381

FOREIGN PATENT DOCUMENTS

52-16016 2/1977 Japan 156/86
1078559 8/1967 United Kingdom 156/86
1410769 10/1975 United Kingdom 285/381

Primary Examiner—Caleb Weston

Attorney, Agent, or Firm—Fisher, Christen & Sabol

[57] ABSTRACT

A process for placing heat-shrinkable polyfluoroolefin polymer sleeves, preferably, FEP resin or PFA resin, over Frasch sulfur well piping and other downhole well piping to protect such piping from corrosion.

A heat chamber for heat-shrinking the polyfluoroolefin polymer sleeves onto the piping.

15 Claims, 9 Drawing Figures

