



US007572430B2

(12) **United States Patent**
Taube et al.

(10) **Patent No.:** **US 7,572,430 B2**
(45) **Date of Patent:** ***Aug. 11, 2009**

(54) **METHOD FOR PRODUCING NANO-PARTICLES**
(75) Inventors: **Joel A. Taube**, Ft. Madison, IA (US);
Mohamed H. Khan, Tucson, AZ (US);
James A. Cole, Ft. Madison, IA (US)
(73) Assignee: **Cyprus Amax Minerals Company**,
Phoenix, AZ (US)
(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 1050 days.

This patent is subject to a terminal dis-
claimer.

4,309,214 A * 1/1982 Foulard et al. 75/345
4,555,387 A * 11/1985 Sabacky et al. 423/59
4,865,832 A 9/1989 Kamijyo
5,045,516 A 9/1991 Vogel et al.
5,185,133 A 2/1993 Scheftic et al.
5,472,749 A 12/1995 Dravid et al.
5,514,350 A 5/1996 Kear et al.
5,665,277 A 9/1997 Johnson et al.
5,698,483 A 12/1997 Ong et al.
5,788,738 A 8/1998 Pirzada et al.
5,804,151 A 9/1998 Sweetser et al.
5,820,844 A 10/1998 Khan et al.
5,851,507 A 12/1998 Pirzada et al.
5,874,684 A 2/1999 Parker et al.
5,879,715 A 3/1999 Higgins et al.
5,922,299 A 7/1999 Bruinsma et al.
6,210,800 B1 4/2001 Nesper et al.
6,468,497 B1 * 10/2002 Khan et al. 423/606

(21) Appl. No.: **10/438,597**

(22) Filed: **May 15, 2003**

(65) **Prior Publication Data**

US 2004/0013602 A1 Jan. 22, 2004

Related U.S. Application Data

(60) Continuation-in-part of application No. 10/222,626,
filed on Aug. 16, 2002, which is a division of applica-
tion No. 09/709,838, filed on Nov. 9, 2000, now Pat.
No. 6,468,497.

(51) **Int. Cl.**
C01G 39/00 (2006.01)

(52) **U.S. Cl.** **423/606**; 977/775; 977/776;
977/811

(58) **Field of Classification Search** 977/773,
977/775, 776, 811; 423/606
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

3,062,638 A * 11/1962 Culbertson et al. 75/367
3,139,326 A * 6/1964 Costello 423/59
3,449,072 A * 6/1969 Freeman 423/304
3,743,708 A * 7/1973 Chase et al. 423/617

OTHER PUBLICATIONS

Chemical Principles, 4th Ed., Masterton & Slowinski, 1977, p. 404.*

* cited by examiner

Primary Examiner—Steven Bos

(74) *Attorney, Agent, or Firm*—Fennemore Craig, P.C.

(57) **ABSTRACT**

Apparatus for producing nano-particles according to the present invention may comprise a furnace defining a vapor region therein. A precipitation conduit having an inlet end and an outlet end is positioned with respect to the furnace so that the inlet end is open to the vapor region. A quench fluid supply apparatus supplies quench fluid in a gas state and quench fluid in a liquid state. A quench fluid port positioned within the precipitation conduit is fluidically connected to the quench fluid supply apparatus so that an inlet to the quench fluid port receives quench fluid in the gas state and quench fluid in the liquid state. The quench fluid port provides a quench fluid stream to the precipitation conduit to precipitate nano-particles within the precipitation conduit. A product collection apparatus connected to the outlet end of the precipitation conduit collects the nano-particles produced within the precipitation conduit.

14 Claims, 5 Drawing Sheets