



US008956724B2

(12) **United States Patent**
Shaw et al.

(10) **Patent No.:** **US 8,956,724 B2**

(45) **Date of Patent:** **Feb. 17, 2015**

(54) **SPHERICAL MOLYBDENUM DISULFIDE POWDERS, MOLYBDENUM DISULFIDE COATINGS, AND METHODS FOR PRODUCING SAME**

(71) Applicant: **Climax Engineered Materials, LLC**,
Phoenix, AZ (US)

(72) Inventors: **Matthew C. Shaw**, Sahuarita, AZ (US);
Carl V. Cox, Sahuarita, AZ (US); **Yakov Epshteyn**, Sahuarita, AZ (US)

(73) Assignee: **Climax Engineered Materials, LLC**,
Phoenix, AZ (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 49 days.

(21) Appl. No.: **13/940,941**

(22) Filed: **Jul. 12, 2013**

(65) **Prior Publication Data**

US 2013/0296204 A1 Nov. 7, 2013

Related U.S. Application Data

(63) Continuation of application No. 13/095,161, filed on Apr. 27, 2011, now Pat. No. 8,507,090.

(51) **Int. Cl.**
C01G 39/06 (2006.01)
C10M 125/22 (2006.01)
(Continued)

(52) **U.S. Cl.**
CPC **C10M 125/22** (2013.01); **C01G 39/06** (2013.01); **C23C 4/04** (2013.01); **C23C 24/04** (2013.01);
(Continued)

(58) **Field of Classification Search**
None
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

2,892,741 A 6/1959 Spengler et al.
3,062,741 A 11/1962 Crowl
(Continued)

FOREIGN PATENT DOCUMENTS

DE 102007029291 A1 12/2008
JP 10226833 A 8/1987
(Continued)

OTHER PUBLICATIONS

Bhattacharya, R.S. et al., "High energy (MeV) ion beam modifications of sputtered molybdenum disulfide coatings on sapphire," Nuclear Instruments & Methods in Physics Research, Section B: Beam Interactions with Material and Atoms, (1991), B59-60, Pt. 2, pp. 788-792.

(Continued)

Primary Examiner — Melvin C Mayes

Assistant Examiner — Colin W Slifka

(74) *Attorney, Agent, or Firm* — Fennemore Craig, P.C.

(57) **ABSTRACT**

Molybdenum disulfide powders include substantially spherically-shaped particles of molybdenum disulfide that are formed from agglomerations of generally flake-shaped sub-particles. The molybdenum disulfide powders are flowable and exhibit uniform densities. Methods for producing a molybdenum disulfide powder may include the steps of: Providing a supply of molybdenum disulfide precursor material; providing a supply of a liquid; providing a supply of a binder; combining the molybdenum disulfide precursor material with the liquid and the binder to form a slurry; feeding the slurry into a stream of hot gas; and recovering the molybdenum disulfide powder, the molybdenum disulfide powder including substantially spherically-shaped particles of molybdenum disulfide formed from agglomerations of generally flake-shaped sub-particles.

11 Claims, 8 Drawing Sheets

